


~~Chem~~Grout Inc.

805 East 31st Street  
P.O. Box 1140  
La Grange Park, Illinois 60525 USA  
Telephone: 708-354-7112  
Fax: 708-354-3881



*CHEM-GROUT*

July 21, 1995

Tom Pelo

Master Builders Technologies

7167 Concord Place

Highlands Ranch, CO 80126

**Re : EMACO T - 430**

The following is our test report on the pumping characteristics of the EMACO T - 430 as tested here at ChemGrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The EMACO T - 430 mixed quickly and thoroughly to a smooth, creamy consistency, and it was pumped without difficulty.

**Conditions :** Inside warehouse temp. 80 Degrees F.

**Equipment Used :** CG-550P Grout pump & mixer, and a 1' X 50' grout hose.

**Mixing Water Temp. :** 68 Degrees F.

**EMACO T - 430 :** Two bags were added to six quarts total water in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "**excellent**" for mixing and pumping through the CG-550P.

Yours truly,

Marvin Hansen  
ChemGrout, Inc.