

**ChemGrout<sup>®</sup>**  
*"Equipment for Grouting"*

ChemGrout, Inc.  
P.O. Box 1140  
805 E. 31st Street  
LaGrange Park, IL  
60526  
Tel: 708-354-7112  
Fax: 708-354-3881

June 15, 1993

Master Builders Technologies  
23700 Chagrin Blvd.  
Cleveland, OH 44122

RE: MASTERFLOW 928 NON-SHRINK, NON-METALIC

The following is the test report on the pumping characteristics of the MASTERFLOW 928 as tested here at Chemgrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The MASTERFLOW 928 mixed quickly and thoroughly to a smooth, creamy consistency and it was pumped without difficulty.

Conditions: Inside Warehouse temp. 68 degrees F.

Equipment Used: CG-550P Grout pump and mixer and a 1" X 50' grout hose.

Mixing Water Temp.: 68 degrees F.

MASTERFLOW 928: Four bags were added to 4 gallons total water in the mixer. With mixer blades running at about 60 RPM a smooth, creamy, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and re-circulated for 5 minutes, and then allowed to sit without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "excellent" for mixing and pumping through the CG-550P.

Yours truly,

Marvin Hansen  
ChemGrout, Inc.