

ChemGrout

Equipment for Grouting

ChemGrout, Inc.
P.O. Box 1140
805 E. 31st Street
LaGrange Park, IL 60526
Tel: 708-354-7112
Fax: 708-354-3881

February 11, 1997
Master Builders Technologies
23700 Chagrin Blvd.
Cleveland, OH 44112

Re: SET 45

The following is our test report on the pumping characteristics of the SET 45 as tested here at ChemGrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The SET 45 mixed quickly and thoroughly to a smooth, creamy consistency and it was not pumped.

Conditions: Inside warehouse temp. 68 Degrees F.

Equipment Used: CG-550P Grout pump & mixer, and a 1" X 50' grout hose.

Mixing Water Temp.: 68 Degrees F.

SET 45: Two bags were added to one gallon total water in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "difficult" for mixing and pumping.

Yours truly,

Marvin Hansen
ChemGrout, Inc.