## **ChemGrout**®

## **Material Testing Results**

August 10, 2000

Paul Abrahamson

612-496-6078

612-496-6078

info@chemgrout.com

Date:

E-Mail:

**Contact:** 

"Equipment for Grouting Since 1969"

805 E. 31st Street, P.O. Box 1140 LaGrange Park, Illinois 60526

**Manufacturer:** ChemRex- Master Builders, Inc.

23700 Chargrin Blvd. Phone: Cleveland, OH 44122 Fax:

**Material:** Shotpatch 21 **Lot** # 12/3/99 M166788779

**Material Application:** Sprayable Wet/Dry Shotcrete Structural Repair Mortar

Mfg. Plant: Houston, TX Std. Bag Weight: 55 #

**Testing Conditions:** Outside Temperature: 82.5\*F Humidity: 61%

**Equipment Used:** Model: CG570 Pump: 2TJ6 Progressing Cavity

Mixer: Paddle Power: Hydraulic

**Std. Mix Ratios**: 5.83 lbs. water per 55 lb bag **Water Temp:** 77.5 \*F

**Batching Method:** Quantity Material: 165 lbs. Quantity Water: 16.0 lbs

Mixing Time: 50-60 Seconds Batch Temp: 88.1 \*F

**Specific Gravity:** SG = N/A **Flow Cone** N/A Seconds

**Pumping Method:** Recirculated through hose, recorded pressures at various flow rates.

Flow Rate/Pressure:	Flow Rate	Pressure	Flow Rate	Pressure
Hose (12.5' Long x 1 1/4" I.D.)	2.53 GPM	0 PSI	GPM	PSI
Hose ( )	4.73 GPM	20 PSI	GPM	PSI
Hose ( )	6.99 GPM	40 PSI	GPM	PSI
Hose ( )	8.49 GPM	45 PSI	GPM	PSI
Hose ( )	10.75 GPM	50 PSI	GPM	PSI
Hose ( )	12.63 GPM	60 PSI	GPM	PSI
Hose ( )	14.51 GPM	65 PSI	GPM	PSI
Hose ( )	16.45 GPM	70 PSI	GPM	PSI
Hose ( )	GPM	PSI	GPM	PSI
Hose ( )	GPM	PSI	GPM	PSI

**Observations:** Dark Grey color, Gritty looking mix, Large particles 1/8" and larger, very thick

very high discharge pressures,

Estimate maximum pumping distance over 50 feet at 5 GPM

**Results:** ChemGrout, Inc. rates the pumpability of this product as a "5" out of 10, with

10 being the easiest. ChemGrout, Inc. recommends the CG2J6 pump or higher.