

# ChemGrout

"Equipment for Grouting"

ChemGrout, Inc.  
P.O. Box 1140  
805 E. 31st Street  
LaGrange Park, IL 60526  
Tel: 708-354-7112  
Fax: 708-354-3881

September 19, 1994  
Mike LeMark  
Conspec  
636 South 66th Street  
Kansas City, KS 66111

Re: CONSPEC SPECIAL PATCH

The following is our test report on the pumping characteristics of the CONSPEC SPECIAL PATCH as tested here at ChemGrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The CONSPEC SPECIAL PATCH mixed quickly and thoroughly to a smooth, creamy consistency, and it was pumped without difficulty.

Conditions: Inside warehouse temp. 68 Degrees F.

Equipment Used: CG-570 Grout pump & mixer, a 1" X 50' grout hose and spray wand.

CONSPEC SPECIAL PATCH: Four bags were added to 24 pints total of Conspec Special Bond Acrylic Laytex material in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

The material was sprayed on a vertical surface. The material stayed on the surface with no movement and very little rebound.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "excellent" for mixing and pumping through the CG-570.

Yours truly,

Marvin Hansen  
ChemGrout, Inc.