

ChemGrout

"EQUIPMENT FOR GROUTING"

GROUT PUMPS & MIXERS • ACCESSORIES • GROUTING SYSTEMS • TECHNICAL ASSISTANCE

October 12, 1993

Steven Gray
Dap Inc.
5300 ~~Huberville Raod~~
Dayton, OH 45431

*2400 Boston St
Suite 200
Baltimore MD, 21224*

Dawn Speckman

Re: Grout Testing Report on 80P Self Leveling Underlayment

The following is our test report on the pumping characteristics of the 80 P Self Leveling Underlayment as tested here at ChemGrout on September 9, 1993. We appreciate very much your confidence in our equipment and the opportunity to be of service.

The 80 P mixed quickly and thoroughly to smooth, creamy consistency, and it was pumped without difficulty.

Conditions: Inside warehouse temp. 68 Degrees F.

Equipment Used: CG-540A Grout pump & mixer, and a 1" ID X 50' Grout hose

Mixing Water Temperature: 68 Degrees F.

80P: 2 bags were added to 13 qts. total water in the mixer. With mixer blades running at about 60-75 RPM a creamy, smooth, lump-free consistency was observed about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "excellent" for mixing and pumping through the CG-540A.

Yours truly,

Marvin Hansen
ChemGrout, Inc.