


ChemGrout Inc.
805 East 31st Street
P.O. Box 1140
La Grange Park, Illinois 60525 USA
Telephone: 708-354-7112
Fax: 708-354-3881



November 7, 1995
John Gill
Dayton Superior
721 Richard Street
Miamisburg, Ohio 45342

Re : LEVEL LAYER I

The following is our test report on the pumping characteristics of the Level Layer I as tested here at ChemGrout on November 7, 1995. We appreciate your confidence in our equipment and the opportunity to be of service.

The Level Layer I mixed quickly and thoroughly to a smooth, creamy consistency, and it was pumped without difficulty.

Conditions : Inside warehouse temp. 68 Degrees F.

Equipment Used : CG-540 Grout pump & mixer, and a 1' X 50' grout hose.

Mixing Water Temp. : 68 Degrees F.

Level Layer I : Two bags were added to 13 quarts total water in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "**excellent**" for mixing and pumping through the CG-540.

Yours truly,

Marvin Hansen
ChemGrout, Inc.