

ChemGrout Inc.  
805 East 31st Street  
P.O. Box 1140  
La Grange Park, Illinois 60525 USA  
Telephone: 708-354-7112  
Fax: 708-354-3881



November 7, 1995  
John Gill  
Dayton Superior  
721 Richard Street  
Miamisburg, Ohio 45342

**Re : LEVEL LAYER II**

The following is our test report on the pumping characteristics of the Level Layer II as tested here at ChemGrout on November 7, 1995. We appreciate your confidence in our equipment and the opportunity to be of service.

The Level Layer II mixed quickly and thoroughly to a smooth, creamy consistency, and it was pumped without difficulty.

**Conditions :** Inside warehouse temp. 68 Degrees F.

**Equipment Used :** CG-540 Grout pump & mixer, and a 1' X 50' grout hose.

**Mixing Water Temp. :** 68 Degrees F.

**Level Layer II :** Two bags were added to 11 quarts total water in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "**excellent**" for mixing and pumping through the CG-540.

Yours truly,

Marvin Hansen  
ChemGrout, Inc.