

ChemGrout®

"Equipment for Grouting"

ChemGrout, Inc.
P.O. Box 1140
805 E. 31st Street
LaGrange Park, IL
60526
Tel: 708-354-7112
Fax: 708-354-3881

July 9, 1997
John Hukey
Dayton Superior
402 South First Street
Oregon, IL 61061

RE: Polyfast FS

The following is the test report on the pumping characteristics of the Polyfast FS as tested here at Chemgrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The Polyfast FS mixed quickly and thoroughly to a thick, pasty consistency and it was pumped & sprayed without difficulty.

Conditions:	Inside Warehouse temp. 68 degrees F.
Equipment Used:	CG-570 Grout pump and mixer, a spray wand and a 1" X 50' grout hose.
Mixing Water Temp.:	68 degrees F.
Polyfast FS:	Four bags were added to four gallons total water in the mixer. With mixer blades running at about 60 RPM a thick, pasty lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped & sprayed and re-circulated for 5 minutes, and then allowed to sit without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "excellent for mixing and pumping through the CG-570.

Yours truly,



Marvin Hansen
ChemGrout, Inc.