

ChemGrout

"Equipment for Grouting"

P.O. Box 1140
805 E. 31st Street
LaGrange Park, IL 60526
Tel: 708-354-7112
Fax: 708-354-3881

January 5, 1995
John Iszczyszyn
Dayton Superior
721 Richard Street
Miamisburg, Ohio 45342

Re : SURE-GRIP HIGH PERFORMANCE ASTM 1107

The following is our test report on the pumping characteristics of the SURE-GRIP ASTM 1107 as tested here at ChemGrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The SURE-GRIP ASTM 1107 mixed quickly and thoroughly to a smooth, creamy consistency, and it was pumped without difficulty.

Conditions : Inside warehouse temp. 68 Degrees F.

Equipment Used : CG-550P Grout pump & mixer, and a 1' X 50' grout hose.

Mixing Water Temp. : 68 Degrees F.

SURE-GRIP ASTM 1107 : Two bags were added to 8 quarts total water in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "excellent" for mixing and pumping through the CG-550P.

Yours truly,



Marvin Hansen
ChemGrout, Inc.