

ChemGrout

Equipment for Grouting

ChemGrout, Inc.
P.O. Box 1140
805 E. 31st Street
LaGrange Park, IL 60526
Tel: 708-354-7112
Fax: 708-354-3881

April 17, 1997
Brian Kaine
Dependable Chemical Co.
P.O. Box 16344
Rocky River, OH 44116

Re: GSL (Gypsum Self Leveling)

The following is our test report on the pumping characteristics of the GSL as tested here at ChemGrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The GSL mixed quickly and thoroughly to a smooth, creamy consistency, and it was pumped without difficulty.

Conditions: Inside warehouse temp. 68 Degrees F.

Equipment Used: CG-550P Grout pump & mixer, and a 1" X 50' grout hose.

Mixing Water Temp.: 68 Degrees F.


GSL: Three bags were added to three gallons total water in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "excellent" for mixing and pumping through the CG-550P.

Yours truly,



Marvin Hansen
ChemGrout, Inc.