

ChemGrout

"Equipment for Grouting"

ChemGrout, Inc.
P.O. Box 1140
805 E. 31st Street
LaGrange Park, IL 60526
Tel: 708-354-7112
Fax: 708-354-3881

August 21, 1996
Bill McCord
Euclid Chemical Company
19218 Redwood Road
Cleveland, Ohio 44110

Re: EUCO SR-VO

The following is our test report on the pumping characteristics of the EUCO SR-VO as tested here at ChemGrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The EUCO SR-VO mixed quickly and thoroughly to a thick, pasty consistency, and it was pumped without difficulty.

Conditions: Inside warehouse temp. 68 Degrees F.

Equipment Used: CG-570 Grout pump & mixer, a 1" X 50' grout hose and a spray wand

Mixing Water Temp.: 68 Degrees F.


EUCO SR-VO: Two bags were added to 1.9 gallons total water in the mixer. With mixer blades running at about 60 RPM a thick, pasty, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "excellent" for mixing and pumping through the CG-570.

Yours truly,



Marvin Hansen
ChemGrout, Inc.