

**ChemGrout Inc.**  
805 East 31st Street  
P.O. Box 1140  
La Grange Park, Illinois 60525 USA  
Telephone: 708-354-7112  
Fax: 708-354-3881



**CHEM@GROUT**

August 25, 1995  
Henry Allen  
Five Star Products, Inc.  
425 Stillson Road  
Fairfield, CT 06430

**Re : NBEC NON-SHRINK GROUT**

The following is our test report on the pumping characteristics of the NBEC as tested here at ChemGrout on this date. We appreciate your confidence in our equipment and the opportunity to be of service.

The NBEC mixed quickly and thoroughly to a smooth, creamy consistency, and it was pumped without difficulty.

**Conditions :** Inside warehouse temp. 68 Degrees F.

**Equipment Used :** CG-550P Grout pump & mixer, and a 1' X 50' grout hose.

**Mixing Water Temp. :** 68 Degrees F.

**NBEC :** Two bags were added to ten quarts total water in the mixer. With mixer blades running at about 60 RPM a creamy, smooth, lump-free consistency was observed after about 30 seconds after the last bag was added.

The batch was pumped and recirculated for 5 minutes, and then allowed to sit in the hopper without movement for 5 minutes. Pumping was resumed without problems.

No discoloration or separation was observed. The material appeared to stay in suspension without significant settlement of aggregate.

ChemGrout considers this product to be "**excellent**" for mixing and pumping through the CG-550P.

Yours truly,

Marvin Hansen  
ChemGrout, Inc.