

ChemGrout®

"Equipment for Grouting Since 1969"

805 E. 31st Street, P.O. Box 1140

LaGrange Park, Illinois 60526

Phone: 708-354-7112 Fax: 708-354-3881

Material Testing Results

Date: August 25, 2000

E-Mail: info@chemgrout.com

Web Site: www.chemgrout.com

Manufacturer: Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071

Contact: Timothy R. Gillespie
Phone: 201-933-8800
Fax: 201-933-6225

Material: SikaTop 122 Plus **Lot #** 062800-L

Material Application: polymer modified, trowel grade mortar with feuroguard
corrosion inhibition

Mfg. Plant: Lynhurst, NJ **Std. Bag Weight:** 61.5 #

Testing Conditions: Outside Temperature: 79.8°F Humidity: 50%

Equipment Used: Model: CG570 Pump: 2TJ6 Progressing Cavity
Mixer: Paddle Power: Hydraulic

Std. Mix Ratios: 1 gal polymer/bag **Polymer Temp:** 79.5 *F

Batching Method: Quantity Material: 3 gal. Quantity Polymer: 3 gal

Mixing Time: 40-50 Seconds **Batch Temp:** 93.5 *F

Specific Gravity: SG = N/A **Flow Cone** N/A Seconds

Pumping Method: Recirculated through hose, recorded pressures at various flow rates.

Flow Rate/Pressure:	Flow Rate	Pressure	Flow Rate	Pressure
Hose (50 ft X 1 1/4in)	3.44 GPM	60 PSI	GPM	PSI
Hose ()	5.21 GPM	80 PSI	GPM	PSI
Hose ()	7.15 GPM	100 PSI	GPM	PSI
Hose ()	9.03 GPM	120 PSI	GPM	PSI
Hose ()	10.75 GPM	140 PSI	GPM	PSI
Hose ()	13.01 GPM	150 PSI	GPM	PSI
Hose ()	14.78 GPM	165 PSI	GPM	PSI
Hose ()	16.5 GPM	190 PSI	GPM	PSI
Hose ()	GPM	PSI	GPM	PSI
Hose ()	GPM	PSI	GPM	PSI

Observations: Mixed and pumped easy—stayed together well—no large particles
High discharge pressure—quick set time
Max hose distance: 25 ft

Results: ChemGrout, Inc. rates the pumpability of this product as a "6" out of 10, with 10 being the easiest. We recommend the 030 or CG2J6 pump or higher.