

ChemGrout®

"Equipment for Grouting Since 1969"

805 E. 31st Street, P.O. Box 1140

LaGrange Park, Illinois 60526

Phone: 708-354-7112 Fax: 708-354-3881

Material Testing Results

Date: Sept. 19, 2012

E-Mail: info@chemgrout.com

Web Site: www.chemgrout.com

Manufacturer: SpecChem, LLC
1619 Walnut Street
Kansas City, MO 64108

Contact: Michael LeMark
Phone: 866-791-8700
Fax:

Material: RepCon 928

Lot # 07271211

Material Application: Rapid Hardening Repair Mortar

Mfg. Plant: Kansas City, MO

Std. Bag Weight: 50 #

Testing Conditions: Outside Temperature: 73.2°F

Humidity: 30%

Equipment Used: Model: CG570
Mixer: Paddle

Pump: 2TJ6 Progressing Cavity
Power: Hydraulic

Std. Mix Ratios: 50 lbs. to 5.25 pints

Water Temp: 68 °F

Batching Method: Quantity Material: 150 lbs.

Quantity Water: 16.5 lbs

Mixing Time: 180 Seconds

Batch Temp: 78 °F

Specific Gravity: SG = 2.12

Flow Cone n/a Seconds

Pumping Method: Recirculated through hose, recorded pressures at various flow rates.

Flow Rate/Pressure:	Flow Rate	Pressure	Flow Rate	Pressure
Hose (1 1/4" x 25')	5.9 GPM	90 PSI	GPM	PSI
Hose ()	9.6 GPM	140 PSI	GPM	PSI
Hose ()	12.9 GPM	170 PSI	GPM	PSI
Hose ()	17.0 GPM	210 PSI	GPM	PSI
Hose ()	18.3 GPM	220 PSI	GPM	PSI
Hose ()	GPM	PSI	GPM	PSI
Hose ()	GPM	PSI	GPM	PSI
Hose ()	GPM	PSI	GPM	PSI
Hose ()	GPM	PSI	GPM	PSI
Hose ()	GPM	PSI	GPM	PSI

Observations: Dark Gray color, gritty looking, some sand settling during washout
Pumped with medium high pressures. Estimate max hose length
of 50 feet

Results: ChemGrout, Inc. rates the pumpability of the product as a "5" out of 10. with
10 being the easiest. ChemGrout, Inc. recommends the CG030 pump or higher.