

"Equipment for Grouting Since 1969" 805 E. 31st Street PO Po -- 1140 L Р

Material Testing Results

| "Equipment for Grouting Since 1969" 805 E. 31st Street, P.O. Box 1140 LaGrange Park, Illinois 60526 | | Date: E-Mail: | Oct 17, 2023 info@chemgrout.com |
|--|---|----------------------------|------------------------------------|
| Phone : 708-354-7112 | Fax : 708-354-3881 | Web Site: | www.chemgrout.com |
| Manufacturer: | SpexCrete 29299 Clemens Rd #1-L Westlake, OH 44145 | Contact: Phone: Fax: | David Schabel 440-462-1500 |
| Material: | SpexCrete 5000 W SLU | Lot # | n/a |
| Material Application: | Self Leveling Underlayment | | |
| Mfg. Plant: | Westlake, OH | Std. Bag Wei | ight: 50 # |
| Testing Conditions: | Outside Temperature: 51*F | Humidity: | 73% |
| Equipment Used: | Model: CG570 Mixer: Paddle | | J6 Progressing Cavity ydraulic |
| Std. Mix Ratios: | | Water Temp | : 63 *F |
| Batching Method: | Quantity Material: 300 lbs. | Quantity Wat | er: 62.5 lbs |
| Mixing Time: | 240 Seconds | Batch Temp: | 65.8 *F |
| Specific Gravity: | SG = 2.08 | Flow Cone | n/a Seconds |
| Pumping Method: | Recirculated through hose, recorded pressures at various flow rates. | | |
| Flow Rate/Pressure: Hose (1 1/4" x 50') Hose () Hose () | Flow RatePressure2.8 GPM37 PSI5.43 GPM75 PSI7.79 GPM107 PSI10.54 GPM137 PSI13.28 GPM160 PSI16.13 GPM175 PSI18.11 GPM185 PSI21.34 GPM205 PSI23.54 GPM210 PSI25.96 GPM215 PSIThick material at start of mixing, snPumped with higher pressure than nsurface with higher density. Estimation | ormal SLU, bu | t this material is a wear |
| Results: | ChemGrout rates the pumpability of this product as a "7" out of 10, with 10 being the easiest. ChemGrout recommends the CG 050 pump or higher. | | |